

WEST**End of Result Set**

Generate Collection

Print

L1: Entry 1 of 1

File: DWPI

Jun 16, 1993

DERWENT-ACC-NO: 1993-215789

DERWENT-WEEK: 199618

COPYRIGHT 2002 DERWENT INFORMATION LTD

TITLE: Synthesis of silico-alumino titanate isomorphous to zeolite beta - by mixing hydrolysed titanium di:oxide in aq. tetra:ethyl:ammonium, silica and e.g. alumina, heating obtd. gel in autoclave and calcining silico-alumino-titanate

PATENT-ASSIGNEE:

ASSIGNEE

UNIV VALENCIA POLITECNICA

CODE

UYVAN

PRIORITY-DATA: 1991ES-0001798 (July 31, 1991)

PATENT-FAMILY:

PUB-NO	PUB-DATE	LANGUAGE	PAGES	MAIN-IPC
<u>ES 2037596 A1</u>	June 16, 1993		000	B01J021/06
<u>ES 2037596 B1</u>	February 16, 1994		000	B01J021/06

APPLICATION-DATA:

PUB-NO	APPL-DATE	APPL-NO	DESCRIPTOR
ES 2037596A1	July 31, 1991	1991ES-0001798	
ES 2037596B1	July 31, 1991	1991ES-0001798	

INT-CL (IPC): B01J 21/06; C07B 33/00

ABSTRACTED-PUB-NO: ES 2037596A

BASIC-ABSTRACT:

Synthesis of silicoaluminotitanate isomorphous to zeolite beta comprises hydrolysing a source of TiO₂ with aq. tetraethylammonium, diluting with water and the prod. soln. hydrolyses the reactive source of Y (e.g. silica). The mixt. obtd. is treated with a soln. contg. a source of X₂O₃ (Al₂O₃ or (NO₃)₃Al) and is autoclaved at 80-120 deg.C.

USE/ADVANTAGE - The prod. is isomorphous to zeolite beta and is activated by calcination at 350-800 deg.C. It can be used for selective oxidn. of organic cpds., esp. for converting alkanes or cycloalkanes to alcohols and ketones, phenol to catechol and hydroquinone and alkenes to epoxides.

TITLE-TERMS: SYNTHESIS SILICO ALUMINO TITANATE ISOMORPHOUS ZEOLITE BETA MIX HYDROLYSIS TITANIUM DI OXIDE AQUEOUS TETRA ETHYL AMMONIUM SILICA ALUMINA HEAT OBTAIN GEL AUTOCLAVE CALCINE SILICO ALUMINO TITANATE

ADDL-INDEXING-TERMS:

SELECTIVE OXIDN. OF ORGANIC CPDS.

DERWENT-CLASS: E19 E32 J04

CPI-CODES: E31-P02A; J04-E04;

SECONDARY-ACC-NO:

POWERED BY **Dialog**

Synthesis of silico-alumino titanate isomorphous to zeolite beta - by mixing hydrolysed titanium dioxide in aq. tetraethylammonium, silica and e.g. alumina, heating obtd. gel in autoclave and calcining silico-alumino-titanate

Patent Assignee: UNIV VALENCIA POLITECNICA

Patent Family

Patent Number	Kind	Date	Application Number	Kind	Date	Week	Type
ES 2037596	A1	19930616	ES 911798	A	19910731	199327	B
ES 2037596	B1	19940216	ES 911798	A	19910731	199411	

Priority Applications (Number Kind Date): ES 911798 A (19910731)

Patent Details

Patent	Kind	Language	Page	Main IPC	Filing Notes
ES 2037596	A1			B01J-021/06	
ES 2037596	B1			B01J-021/06	

Abstract:

ES 2037596 A

Synthesis of silicoaluminotitanate isomorphous to zeolite beta comprises hydrolysing a source of TiO₂ with aq. tetraethylammonium, diluting with water and the prod. soln. hydrolyses the reactive source of Y (e.g. silica). The mixt. obtd. is treated with a soln. contg. a source of X₂O₃(Al₂O₃ or (NO₃)₃AL) and is autoclaved at 80-120 deg.C.

USE/ADVANTAGE - The prod. is isomorphous to zeolite beta and is activated by calcination at 350-800 deg.C. It can be used for selective oxidn. of organic cpds., esp. for converting alkanes or cycloalkanes to alcohols and ketones, phenol to catechol and hydroquinone and alkenes to epoxides.

Derwent World Patents Index

© 2002 Derwent Information Ltd. All rights reserved.

Dialog® File Number 351 Accession Number 9522248